

SR.G-FLEX™

FLEXIBLE EXPANDED POLYSTYRENE INSULATION

The flexible SR.G-Flex™ insulating boards manufactured by Styro Rail Inc. are composed of type 2 or type 3 expanded polystyrene laminated on each side by a polypropylene membrane.



CHARACTERISTICS

BOARD OFFERS A GREATER FLEXIBILITY

SUPERIOR RESISTANCE TO DAMAGE

G-LOCK™ SHIP LAP MAINTAINS THE BOARDS FIRMLY IN PLACE

REPOSITIONNABLE BOARD

CONFORMS TO GROUND IRREGULARITIES

MEETS CAN/ULC-S701.1 STANDARD



SR.G-FLEX™ **FLEXIBLE EXPANDED POLYSTYRENE INSULATION**

AVAILABLE DIMENSIONS

			200	300	350	
1219 mm x 2438 mm	[48" x 96"]	30 mm	[1-3/16"]	R5.0	R5.0	
1219 mm x 2743 mm	[48" x 108"]	32 mm	[1-1/4"]	R5.0*		
G-Lock™ system on four sides.		46 mm	[1-13/16"]	R7.5	R7.8	
		48 mm	[1-7/8"]	R7.5*		
		59 mm	[2-5/16"]			R10
		60 mm	[2-3/8"]		R10.0	
		64 mm	[2-1/2"]	R10.0		

* In stock

RECOMMENDED USE

Install the **SR.G-Flex™** boards underneath the finished basement concrete slab and of residential and commercial garage concrete slabs. Ideal when the backfill material is uneven – the boards stay interconnected to one another through the G-Lock™ ship lap system and the flexibility of the board.

CERTIFICATION

Warnock Hersey has certified the type 2 and type 3 expanded polystyrene contained in **SR.G-Flex™** boards in accordance with the CAN/ULC-S701.1 standard. The type 2 and type 3 expanded polystyrene produced by STYRORAIL™ is listed in the CCMC Registry of Product Evaluation under CCMC 13271-L and CCMC 13277-L.

ENVIRONMENTAL DATA

The expanded polystyrene used in the making of the **SR.G-Flex™** boards are composed of 98% air and 2% plastic material. They are manufactured without HCFC, HFC gases and without HBCD flame retardant.

The STYRORAIL™ products can contribute to LEED credits.

Please send us your LEED Material Declaration Form at projetleed@styrorail.ca.

STORAGE

Store **SR.G-Flex™** boards in a dry and ventilated location, protected from the outside elements, ultraviolet rays, open flames or other sources of ignition. Stack boards on pallets of minimum 100 mm [4"] over the ground.

INSTALLATION

Boards must be dry and in good condition before installation.

Refer to the *Installation Guide* for more information.

LIMITATIONS

Expanded polystyrene is combustible. Even if expanded polystyrene contains a flame retardant, limit use of open flame or ignition sources near product. A protective barrier or thermal barrier is required as specified in the appropriate building code.

Expanded polystyrene may be affected by some oil based solvents.

EXEMPTION OF LIABILITY

The information herein is based on the present state of our best scientific and practical knowledge. The user is responsible for checking the suitability of products for their intended use. STYRORAIL™ technical data sheets are updated on a regular basis; it is the user's responsibility to obtain and to confirm the most recent version. Information contained in this data sheet may change without notice.

SR.G-FLEX™ **FLEXIBLE EXPANDED POLYSTYRENE INSULATION**

PHYSICAL PROPERTIES

INSULATING BOARD	200	300	350	POLYETHYLENE VAPOR BARRIER*	
Type	2	3	3	Tensile Strength [ASTM D882]	MD** 2109 kg/cm ³ [30 000 lbs/in ²]
Thermal Resistance Min. [ASTM C518] Thickness of 25 mm [1"]	RSI 0,70 [R4.0]	RSI 0,74 [R4.2]	RSI 0,76 [R4.3]	CD 2109 kg/cm ³ [30 000 lbs/in ²]	
MVTR Max. [ASTM E96]	200 ng/Pa-s-m ² [3.5 US Perms]	130 ng/Pa-s-m ² [2.27 US Perms]	130 ng/Pa-s-m ² [2.27 US Perms]	Elongation [ASTM D882]	MD 85%
Compressive Strength Min. [ASTM D1621] 10% Deformation	110 kPa [16 PSI]	140 kPa [20 PSI]	210 kPa [30 PSI]	CD 115%	
Flexural Strength Min. [ASTM C203]	240 kPa [35 PSI]	300 kPa [44 PSI]	345 kPa [50 PSI]	Elasticity Limit	30 000 in ² /lbs
Water Absorption Max. [ASTM D2842] Volume	2 %	2 %	1.8 %	Water Vapor Transmission Rate [ASTM F1249]	0.6 gms/100in ² /24h [0.00053 US Perm]
Dimensional Stability Max. [ASTM D2126] Linear Variation	1.5 %	1.5 %	1.5 %	Sealing Temperature	220-250°F [104-121°C]
Limiting Oxygen Index Min. [ASTM D2863]	24 %	24 %	24 %	Friction Coefficient [ASTM D1894] Face to face	0.4-0.5
Density Min. [ASTM C303]	20 kg/m ³ [1.2 lbs/ft ³]	25 kg/m ³ [1.5 lbs/ft ³]	29 kg/m ³ [1.8 lbs/ft ³]	Thickness ± 5%	1.0 mil
Flame Spread Rating [CAN/ULC S102.2]	145	145	145	* Data provided by the manufacturer. ** MD Machine Direction, CD Cross Machine Direction	